



e-ISSN: 2319-8753 | p-ISSN: 2347-6710

IJRSET

International Journal of Innovative Research in
SCIENCE | ENGINEERING | TECHNOLOGY

INTERNATIONAL JOURNAL OF INNOVATIVE RESEARCH

IN SCIENCE | ENGINEERING | TECHNOLOGY

Volume 12, Issue 7, July 2023

ISSN INTERNATIONAL
STANDARD
SERIAL
NUMBER
INDIA

Impact Factor: 8.423

9940 572 462

6381 907 438

ijirset@gmail.com

www.ijirset.com

Degradation of Persistent Organic Pollutants from Contaminated Wastewater Using Photocatalytic Processes- A Literature Review

Mr. Sahil Ghurde ¹, Prof. Anurag K. Gahalod ²

P.G. Student, Department of Civil Engineering, G. H. Rasoni University, Amravati, Maharashtra, India¹

Associate Professor, Department of Civil Engineering, G. H. Rasoni University, Amravati, Maharashtra, India²

ABSTRACT: Wastewaters frequently contain harmful natural poisons with a potential unfriendly impact on human wellbeing and oceanic life upon openness. Constant natural toxins like colors and pesticides, drugs, and different synthetic substances are acquiring broad consideration. Water treatment using photocatalysis has as of late gotten a great deal of interest. Photocatalysis is bleeding edge, elective innovation. It enjoys different benefits, including working at ordinary temperatures and climatic tension, modest costs, no auxiliary waste creation, and being promptly accessible and effectively open. This survey introduced an exhaustive outline of the advances in the use of the photocatalytic cycle in the treatment of exceptionally contaminated modern wastewater. The investigation of different writing uncovered that TiO₂- based photocatalysts are exceptionally successful in debasing natural contaminations from wastewater contrasted with different types of wastewater treatment innovations. The electrical construction of a semiconductor assumes an imperative part in the photocatalyst's component. The morphology of a not set in stone by the union strategy, compound substance, and specialized attributes. The increased of the photoreactors will fundamentally help in controlling the impact of natural toxins in wastewater.

KEYWORDS: Titanium Oxide, Photocatalyst, Photoreactor, Waste water

I. INTRODUCTION

The planet is generally made out of water, which is the most pivotal part of life. Water is important for the presence of all living creatures on The planet. It represents 71% of the world's surface (Panchal et al. 2019). Water has the actual characteristics of being clear, bland, scentless, and drab (Sronsri et al. 2020). It very well may be dirtied by a scope of toxins and contamination sources, including (Aarthy and Sureshkumar 2021). Hazardous substances are utilized in human exercises (modern squanders, composts, pesticides, and so forth) (Akhil et al. 2021) normal minerals what's more, mixtures like arsenic, normal salt, and fluorides Microorganisms or illness causing living beings like single adaptable cells, microbes, furthermore, infections, as well as toxins that effect taste, smell, furthermore, variety. Water treatment is characterized as the most common way of making water significant and satisfactory for a specific end-use, as well as disposing of and bringing down the groupings of water contaminations to match its expected reason (Akpe et al. 2020). The sum furthermore, sort of wastewater treatment methodology not set in stone by the first wastewater's quality, the various posttreatment needs, and the planned end-use. The purging of water sources is one of the main worries influencing the globe today. As per the World Wellbeing Association (WHO), 844 million individuals need admittance to safe drinking water, with 159 million depending on surface water (Al-Gamal et al. 2021). The extent of the water contamination issue is huge, with expansive region of the world experiencing unfortunate water quality.

Water tainting has become one of the most squeezing issues lately because of populace increment and modern turn of events (World Wellbeing Association 2017). Detachment is commonly used to decontaminate water defiled with lipids, disintegrated particles, suspended solids, natural particles, and radioactive mixtures (Lin et al. 2020). Water treatment utilizes different state of the art procedures, including film filtration, particle trade, warm refining, switch assimilation, and nanofiltration.

II. LITERATURE REVIEW

1. Fujishima et al. 2008; Castellote & Bengtsson 2011; Primo & Garca 2013; Ameta et al. 2018

Photocatalysis was defined by researchers (Fujishima et al. 2008; Castellote & Bengtsson 2011; Primo & Garca 2013; Ameta et al. 2018) as an advanced oxidation process (AOP) that changes the rate of a chemical reaction or its initiation in the presence of a photocatalyst. Without being consumed, a photocatalyst may absorb light and perform repetitive

chemical changes of reaction patterns. It becomes involved in the intermediate processes and regenerates after each contact cycle. In other words, a photocatalyst can convert photon energy to chemical energy, which may then be used to alter chemical molecules.

2. Fujishima et al. 2000; Akolekar et al. 2002; Malato et al. 2009; Fagan et al. 2015

The most often used and well-studied photocatalyst is TiO₂ (Fujishima et al. 2000; Akolekar et al. 2002; Malato et al. 2009; Fagan et al. 2015). It is non-toxic, photo-stable, chemically and mechanically stable. Because of its availability, it is also a cheap material. TiO₂ has a significant bandgap and hence a high oxidation potential of about +3.0 V (Akolekar et al. 2002; Fujishima et al. 2000), and it can only be activated by high intensity UV light with wavelengths shorter than 387.5 nm (Figure 2-7) (Malato et al. 2009). Although UV light accounts for a minor portion of solar irradiation, it is nonetheless beneficial for initiating photocatalytic processes on a TiO₂ based photocatalyst (Fagan et al. 2015).

3. Alfano et al., 1970

Titanium dioxide is appealing due to this property, as well as its low toxicity and corrosion resistance (Alfano et al., 1970). Titanium dioxide is classified as a semiconductor because it requires ultraviolet light to drive electrons through the energy gap and into the conduction band. These electrons can then breakdown organic molecules by forming hydroxyl radicals. Many research on the use of TiO₂ as a photocatalyst for the breakdown of organic molecules have been reported. TiO₂ is active in the presence of UV radiation. Photocatalytic activity (PCA) is a material's capacity to generate an electron hole pair in response to UV light. The resultant free radicals are excellent organic matter oxidizers.

4. Xu Zhao et al., 2007; Efthalia C. et al., 2007; C. Fotiadis et al., 2007; A.R. Mohamed et al., 2004; Heqing Tang et al., 2008

They state that under UV light, titanium dioxide, particularly in the anatase form, acts as a photocatalyst. Titanium dioxide has recently been discovered to behave as a photocatalyst under visible and UV light when spiked with nitrogen ions or doped with metal oxides such as tungsten trioxide. The positive holes' high oxidative potential oxidises water, producing hydroxyl radicals. It can also directly oxidise oxygen or organic molecules. It is also employed in the Graetzel cell.

5. Navarro et al. (2009)

They investigated the photodegradation of eight pesticides (azoxystrobin, hexaconazole, kresoxim-methyl, tebuconazole, pyrimethanil, triadimenol, primicarb, propyzamide) in leaching water using tandem ZnO/Na₂S₂O₈ as photosensitizer/oxidant and compound parabolic collectors under natural light. The pesticides vanished using first-order kinetics based on the Langmuir curve, and total breakdown happened within 120 minutes. In each example, the disappearance time (DT₇₅), also known as the normalised illumination time (t_{30W}), was less than 3 minutes [49]. Alalm et al. (2015) studied the effectiveness of solar heterogeneous TiO₂ photocatalysis and homogeneous photo-Fenton reaction for the removal of Lambda Cyhalothrin, Chlorpyrifos, and Diazinon from pesticide wastewater.

6. Hincapie et al. (2005)

They investigated pesticide degradation on a pilot plant scale utilising photo-Fenton and TiO₂ photocatalysis powered by solar radiation. TOC mineralization was used to assess two different iron concentrations. The study employed *Vibrio fischeri* (Microtox1) toxicity tests. Almost 100% mineralization and detoxification were achieved. The detection of chloride was revealed to be an essential metric for predicting the toxicity of chlorinated chemicals [9]. Malato et al. (2003) investigated the photocatalysis of four pesticides (methomyl, diuron, formetanate, and imidacloprid) on a pilot scale in two systems: two-phase catalysis with titanium dioxide and one-phase catalysis by photo-Fenton in the presence of natural-solar UV radiation. The parent chemicals were completely removed with 90% mineralization, and toxicity was reduced below the threshold (EC₅₀) for all pesticides studied.

7. Berberidou et al. (2016)

They investigated an alternate strategy for the treatment of pesticide-contaminated water and artificial wetlands. This integrated system based on solar photocatalysis and artificial wetlands has the potential to successfully detoxify pesticide-containing wastewater, resulting in a cleansed effluent that might be reused [10]. Fenoll et al. (2012) studied the photocatalytic degradation of three chloroacetanilides (propachlor, s-metolachlor, and alachlor) and five s-triazines (simazine, prometryn, terbuthryn, atrazine, and terbuthylazine). Under sunlight, zinc oxide and titanium dioxide were employed as semiconductors in prototype plants. The addition of Na₂S₂O₈ to the semiconductor suspensions increased the photooxidation rate. ZnO was discovered to be the most effective herbicide removal catalyst among all those tested. The results showed that after 4 hours of light in the chosen system, 70% of the herbicide amount was destroyed.

8. Moreira et al. (2012)

They showed the treatment of pesticide-containing wastewater coming from the washing of phytopharmaceutical plastic containers using an immobilised biomass reactor (IBR) and advanced oxidation processes (AOPs). A solar pilot plant was used to investigate heterogeneous (TiO₂/UV and TiO₂/H₂O₂/UV, both with and without acidification) and homogeneous (UV, H₂O₂/UV, Fe²⁺/H₂O₂/UV, and Fe²⁺/H₂O₂ systems). The wastewater had a moderate organic load and excellent biodegradability, and nineteen pesticides in the range of 0.02-45 mg L⁻¹ were measured, accounting



for 14-19% of total DOC. Malato et al. (2007) mineralized a combination of five pesticides, Cymoxanil, Dimethoate, Oxamyl Methomyl, and Pyrimethanil, in a combined solar photocatalytic-biological pilot plant. Two advanced oxidation processes (AOPs: TiO₂ and photo-Fenton) were utilised to improve wastewater biodegradability, and an immobilised biomass reactor (IBR) was used for continuous biological treatment. TiO₂ photocatalysis studies were conducted in a small (35 L) solar pilot plant comprised of just three compound parabolic collectors (CPCs), whereas photo-Fenton testing were conducted in a considerably larger (75 L) solar pilot plant comprised of four CPCs units. The pesticide concentrations in the combination were initially 50 mg L⁻¹ each. The TiO₂ catalyst concentration utilised was 200 mg L⁻¹, while the photo-Fenton assays used two different Fe²⁺ concentrations, 20 mg L⁻¹ and 55 mg L⁻¹. Toxicity (*Vibrio fischeri*) and biodegradability (Zahn-Wellens test) experiments were also carried out to track the toxicity and biodegradability of samples at various phases of photo-Fenton treatment. The combined system removed all contaminants completely, with greater than 90% mineralization and full nitrification.

9. Alista et al.

Photo-Fenton and heterogeneous photo catalysis were reported to be beneficial in decreasing pesticide residues in water by Alista et al. The usage of semiconductors like ZnO and TiO₂ in conjugation with Na₂S₂O₈ (as an oxidant) was certainly extremely efficient in mineralization, and the conversion rate was around 1.3 times higher with ZnO/Na₂S₂O₈ treatment than with TiO₂/Na₂S₂O₈ treatment.

Recent research has focused on the photo catalytic degradation of 2,4-dinitrophenol using a hybrid material consisting of Bi / Bi₂O₃ / C. In the degradation of 2,4-DCP, the photo oxidation rate of Bi / C-2 was found to be 1.60-fold that of Bi₂O₃ and 2.47-fold that of g-C₃N₄. Hybrid catalysts are also exceedingly stable, with photo catalytic activity lasting four cycles in a row. Improved photo catalytic efficiency can be attributed to better light absorption, faster transfer and separation of photo generated carriers, and the SPR impact of metallic bi and conductive carbon support. Oxidative holes are the primary active species in the photochemical reaction cycle of Bi / C-2, however hydroxyl and superoxide radicals can also play supporting roles during photo degradation.

10. Macha et al.

They examined the heterogeneous photocatalysis of organic contaminants in municipal wastewater using TiO₂ and TiO₂ plus metals (Ag, Cu, and Fe) photocatalysts under UV and solar light. The results show that the photocatalysts were effective under both UV and UV-Vis irradiation, with degradation levels more than 95%, overcoming the constraint that the TiO₂ catalyst was only effective under UV light.

III. METHODOLOGY


Materials

The titanium dioxide (TiO₂), with the purity of 99%, (Merck KGaA, Darmstadt, Germany) was used in this study. Ethyl lactate, phenol, copper sulphate, sodium hydroxide, and hydrochloric acid were obtained from Merck (USA). All chemicals used are of reagent grade.


Methodology

The photoreactor is a vessel made of Pyrex glass. This vessel is thermostated at 25oC by a water jacket. The oxygen, air or nitrogen gas was bubbled at a rate 300ml/min through a gas tube located in the reactor. The solution volume is 450 ml. A magnetic bar ensures the TiO₂ particles mixed with the solution completely. A 30 W low pressure mercury lamp with a wavelength of 254nm and a intensity of 18.0mW/cm² (Aquafine Corporation, U.S.A.) was used.

All suspensions of TiO₂ in this research project were stirred with a magnetic bar in a reservoir under dark conditions for approximately 20 minutes before illumination for adsorption to take place. In the adsorption study, the concentrations of organic compounds were found to be nearly stable. In order to get a stable wavelength, the UV lamp was warmed up for about 10 minutes before experiments.



Schematic of photoreactor used in this study



A schematic of the equipment layout of the microencapsulation process.

IV. CONCLUSION

Photocatalytic processes have gained huge headway in the treatment of profoundly tainted modern wastewater, as per this survey. The survey of the distributed articles uncovered that TiO₂- based photocatalysts beat elective wastewater treatment photocatalytic frameworks in corrupting natural pollutants. The union method, synthetic creation, and specialized characteristics all have an influence on the photocatalyst's physicochemical properties. Natural impurities in wastewater can be significantly diminished assuming photoreactors are expanded in size. Utilizing the photocatalysts, the contaminations are changed into CO₂ furthermore, H₂O₂. TiO₂ is one of the most usually used impetuses in the cycle, despite the fact that there are numerous different sorts of impetuses. The photoreactor arrangement should be streamlined to improve the photocatalytic execution with the additional parts to accomplish a legitimate harmony between the treated arrangement volume what's more, the poison amount eliminated toward the finish of the cycle. Moreover, testing conditions ought to be steady to diminish testing blunders across a few works. The utilization of sun based light-determined photocatalysis for ecological remediation ought to be widened to include fresher regions, for example, CO₂ decrease and N₂ obsession. By and large, photocatalysis controlled by sun based light is quite possibly of the most encouraging innovation for handling worldwide energy deficiencies and contamination. Future examination ought to zero in on the production of pilot-plant studies that utilization real wastewater under genuine circumstances to assess the treatment framework's adequacy with regards to contamination corruption rate as well as monetary viewpoints.

REFERENCES

- [1] Bharagava, R. N. 2020 Emerging Eco-Friendly Green Technologies for Wastewater Treatment. Springer, Singapore.
- [2] Chanu, L. A., Singh, W. J., Singh, K. J. & Devi, K. N. 2019 Effect of operational parameters on the photocatalytic degradation of Methylene blue dye solution using manganese doped ZnO nanoparticles. Results in Physics 12, 1230–1237.
- [3] Al-Ghouti, M. A., Al-Kaabi, M. A., Ashfaq, M. Y. & Da'na, D. A. 2019 Produced water characteristics, treatment and reuse: a review. Journal of Water Process Engineering 28, 222–239.
- [4] Bloh, J. Z. 2019 A holistic approach to model the kinetics of photocatalytic reactions. Frontiers in Chemistry 7, 128.
- [5] Binas, V., Stefanopoulos, V., Kiriakidis, G. & Papagiannakopoulos, P. 2019 Photocatalytic oxidation of gaseous benzene, toluene and xylene under UV and visible irradiation over Mn-doped TiO₂ nanoparticles. Journal of Materiomics 5 (1), 56–65.
- [6] Ameta, S. & Ameta, R. 2018 Advanced oxidation processes for wastewater treatment: emerging green chemical technology: Academic Press, Cambridge, MA.
- [7] Ani, I., Akpan, U., Olutoye, M. & Hameed, B. 2018 Photocatalytic degradation of pollutants in petroleum refinery wastewater by TiO₂-and ZnO-based photocatalysts: recent development. Journal of Cleaner Production 205, 930–954.
- [8] Andreozzi, M., Álvarez, M. G., Contreras, S., Medina, F., Clarizia, L., Vitiello, G., Llorca, J. & Marotta, R. 2018 Treatment of saline produced water through photocatalysis using rGO-TiO₂ nanocomposites. Catalysis Today 315, 194–204.
- [9] Al-Sabahi, J., Bora, T., Al-Abri, M. & Dutta, J. 2017 Efficient visible light photocatalysis of benzene, toluene, ethylbenzene and xylene (BTEX) in aqueous solutions using supported zinc oxide nanorods. PloS One 12 (12), e0189276.
- [10] Ansari, S. A., Khan, M. M., Ansari, M. O. & Cho, M. H. 2016 Nitrogen-doped titanium dioxide (N-doped TiO₂) for visible light photocatalysis. New Journal of Chemistry 40 (4), 3000–3009.



- [11]Chen, X., Li, L., Zhang, W., Li, Y., Song, Q. & Dong, L. 2016 Fabricate globular flower-like CuS/CdIn₂S₄/ZnIn₂S₄ with high visible light response via microwave-assisted one-step method and its multipathway photoelectron migration properties for hydrogen evolution and pollutant degradation. ACS Sustainable Chemistry & Engineering 4 (12), 6680–6688.



SJIF Scientific Journal Impact Factor

Impact Factor: 8.423



INTERNATIONAL JOURNAL OF INNOVATIVE RESEARCH

IN SCIENCE | ENGINEERING | TECHNOLOGY

 9940 572 462  6381 907 438  ijirset@gmail.com



www.ijirset.com

Scan to save the contact details